

## **Data Sheet**

## **ENVIROSET 4115**

Two Pack 100% Solids Epoxy Pool Coating

PRODUCT DESCRIPTION	<b>ENVIROSET 4115</b> is a two-pack pigmented, solvent free 100% solids epoxy with excellent surface hardness and adhesion. It exhibits high water resistance, chemical and oil resistance. It has been optimised for vertical application.				
USES & BENEFITS	and also for a	Limitations s an intermediate coat subsequent topcoat mance coating mard wearing  Limitations  1. Amine bloom may occur if humidity is above 80%.  2. Minimum surface temperature should be at least 5°F above dew			
PHYSICAL PROPERTIES	Vehicle Type	Ероху			
	Hardener	Amine			
	Mixing Ratio	4:1(Part A : Part B) by Weight			
	Pot Life	Approx. 1 hour @77ºF. Must be mixed thoroughly			
	Finish	Gloss, slightly textured			
	Theoretical Coverage	165 – 250 sq ft/US gal @ 6 – 10 mil DFT - WFT (4-6m² per litre @160-250μmDFT (160-250μmWFT))			
	Volume Solids	100%			
	Recommended DFT	6 -10 mil /coat (160-250 μm/coat). Dependent on application			
	Usual No. of Coats	2-3 (dependent on substrate)			
	Primer Required	Dependent on substrate. Contact PnF technical team for specifications			
	Colour	Standard Range of Colours			
	Pigmentation	Titanium dioxide and other pigments			
	Product Weight	13 – 14 lbs per Us Gal (1.60 – 1.69 Kg/Litre), depending on pigmentation			

## PaintnForget USA Operations

P: 3213105346 E: <a href="mailto:chris@paintnforget.com">chris@paintnforget.com</a> W: paintnforget.com
Hitchins Australia Pty Ltd P O Box 3186 Bonnells Bay NSW Australia 2264



					and a second a second second	
ENGINEERING DATA	Abrasion Resistance	Very good				
	Chemical Resistance	Contact us for specific recommendations. Resistant to a wide range of acids and alkalis, vegetable and mineral oils. Not resistant to strong oxidizing acids, phenols or amines				
	Dry Heat Resistance	Up to 248ºF				
	Solvent Resistance	Excellent for many solvents				
	Durability	Excellent, but will chalk under UV exposure without damage to the integrity of the coating				
CURING DATA	Substrate Temp.(ºC)	Touch Dry	Light foot traffic	Full Cure	Recoat Time min	
	Standard Hardener 77 ºF	6 Hrs	24 Hrs	6 Days	16 Hrs	
	Note	Maximum recoat varies with the environmental conditions and the topcoat used				
Mixing	Power stir Pack A, then blend with Pack B to correct ratio. Power stir thoroughly for one to two minutes prior to use. Only mix required amount and use within the stated pot life.					
Application	5/8 <sup>th</sup> – 2 ins (10-25mm) Nap Roller.					
Thinning	If required, use Methylated Spirits or V122 Epoxy Thinners.					
Cleaning	Use V105 for clean-up.					
Concrete	New concrete should be allowed to cure for 28 days prior to coating. Surface must be sound, dry, free from all loose material, laitance, old coatings, dust and surface contaminants (e.g. oil, grease, chemicals, release/curing agents etc.). Smooth or contaminated surfaces must be mechanically treated by abrasive blasting or grinding to achieve a clean anchor pattern for best adhesion. Oily surfaces must be detergent cleaned and water blasted. In some instances, acid etch and water blasting may be adequate to form a 'key' for sufficient adhesion. We would recommend the concrete be primed with Enviroset 2100 prior to the application of the ENVIROSET 4115. Please note that moisture content in the concrete must be no greater than 4% prior to application of the E4115. Ensure there's no hydrostatic pressure present.					
Previously coated surfaces	If the previous coating is in good condition, prepare by sanding with #100 grit sandpaper. All surfaces should be free from oil, grease, loose paint and other contaminants.					
General	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with PnF recommended cleaner. Once units of paint have been mixed, they should not be resealed, and it is advised that after prolonged stoppages work recommences with freshly mixed units.					

## PaintnForget USA Operations

P: 3213105346 E: <a href="mailto:chris@paintnforget.com">chris@paintnforget.com</a> W: paintnforget.com



Clean Up	Clean all equipment after use with recommended cleaner. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time (including delays).
Packing	Available in 5 Kg (11lb) kits. For other sizes, contact us.
Storage	12 months if stored in sealed containers away from heat and moisture above 50°F. Subject to re-inspection thereafter.

All applicable statutory regulations must be observed in the application of this product. Users must first read the Material Safety Data Sheet for ENVIROSET 4115. Users should familiarise themselves with all the safety aspects of the product prior to use. Please ensure the current Technical Data Sheet is consulted prior to specification or application of products. We will in many instances provide

Area Specific Instruction Sheets which contain detailed instructions on how to achieve desired results for specific areas. If the surface intended to be painted differs from the specification, please consult the technical team of PaintnForget



P: 3213105346 E: <a href="mailto:chris@paintnforget.com">chris@paintnforget.com</a> W: paintnforget.com
Hitchins Australia Pty Ltd P O Box 3186 Bonnells Bay NSW Australia 2264

PaintNForget Products are for professional and /or industrial use only. Keep container tightly closed. Keep out of reach of children. Not for internal consumption. All users must always read and follow warnings and instructions on the most current product label, Product Data Sheet and Safety Data Sheet which are available online at paintnforget.com.